

LIDDING FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

LFO-6APET

STANDARD THICKNESS - 2.2 MIL

LFO-6APET is a heat sealable lidding film with a specialty sealant on a PET substrate designed for tight to lock seal of a variety of trays. This film is laminated to a 92 GA PET top layer.

Key Features

- Good moisture and oxygen barrier
- One side sealable
- Tight, lock seal to PET substrates

| PROPERTIES | UNIT | TESTING METHOD | TYPICAL VALUES |
|---------------------|-----------------------------|----------------------------|----------------|
| PHYSICAL | | | |
| Yield | in ² /lb | | 9,200 |
| COF Sealant side | | ASTM D1894 | 0.3 |
| Heat resistant side | | | 0.55 |
| BARRIER | | | |
| MVTR | g/100 in ² /day | ASTM F1249 38°C, 100%RH | 0.5 |
| OTR | cc/100 in ² /day | ASTM D3985 23°C, 0%RH | 3.30 |
| THERMAL | | | |
| Shrinkage | % | ASTM D1204 | 1.7 |
| MD | | | |
| TD | | | |

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.