


LAMINATION FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

FPL-200-AF

STANDARD THICKNESS - 2.1 MIL

FPL-200 is a high barrier, peelable lidding film. This lidding film gives excellent seal-peel performance on APET, CPET, PVC, PP and PS containers.

Key Features

- High oxygen barrier
- Suitable for food contact and can also be used for HPP applications
- Great as lidding material for fresh or frozen foods
- Anti Fog Properties for improved aesthetics and presentation of products.
- Optimal sealing temperature: is 375-390 F

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
MECHANICAL			
Tensile Strength MD TD	lb/in ²	ASTM D882	9,000 9,500
Elongation MD TD	%	ASTM D882	125 115
PHYSICAL			
Yield	in ² /lb		12,300
COF Sealant side Heat resistant side		ASTM D1894	<.40 0.5
Haze	%	ASTM D1003	20-22
BARRIER			
MVTR	g/100 in ² /day	ASTM F1249 38°C, 100%RH	0.26
OTR	cc/100 in ² /day	ASTM D3985 23°C, 0%RH	0.6
THERMAL			
Recommended Sealing Temperature	F		365-410°

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.