


## LAMINATION FILMS



### TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

### CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.  
1762 State Route 131  
Milford, Ohio 45150  
P - 800.634.3355  
F - 513.248.8300

www.goldeneagleextrusions.com  
info@goldeneagleextrusions.com

# FPL-200HCA

## STANDARD THICKNESS - 2.0 MIL

**FPL-200HCA** is an ultra high barrier and heat sealable lidding film with a specialty PE based sealant layer. This lidding film is designed as a peelable seal to multiple substrates.

### Key Features

- Excellent moisture and oxygen barrier
- Excellent clarity
- One side sealable
- Plain or printed

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
<b>MECHANICAL</b>			
Tensile Strength MD TD	lb/in <sup>2</sup>	ASTM D882	11,400 10,900
Elongation MD TD	%	ASTM D882	120 110
<b>PHYSICAL</b>			
Yield	in <sup>2</sup> /lb		12,600
COF Sealant side Heat resistant side		ASTM D1894	<.50 0.55
Haze	%	ASTM D1003	4-6
<b>BARRIER</b>			
MVTR	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 100%RH	<0.1
OTR	cc/100 in <sup>2</sup> /day	ASTM D3985 23°C, 0%RH	<0.1
<b>THERMAL</b>			
Recommended Sealing Temperature	F		284-320°

**Disclaimer:** Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.