

LIDDING FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

HB-ACP16

STANDARD THICKNESS - 1.6 GAUGE

HB-ACP16 is a structure consisting of a saran coated PET laminated to a cast polypropylene. This material can be used as a lidding structure or on a VFFS/HFFS.

Key Features

- Excellent moisture and oxygen barrier
- Suitable for “see through” packaging structure
- One side sealable
- Weld seal to PP

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
MECHANICAL			
Tensile Strength MD TD	lb/in ²	ASTM D882	11,600 10,600
Elongation MD TD	%	ASTM D882	100 119
PHYSICAL			
Yield	in ² /lb		16,000
COF Sealant side Heat resistant side		ASTM D1894	< 0.3 0.5
Haze	%	ASTM D1003	5.0
BARRIER			
MVTR	g/100 in ² /day	ASTM F1249 38°C, 100%RH	0.3
OTR	cc/100 in ² /day	ASTM D3985 23°C, 0%RH	0.6

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.