


LAMINATION FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

LAM-15

STANDARD THICKNESS - 1.5 MIL

LAM-15 is a medium barrier, multi-purpose film lamination which is perfectly suited as a pouch material or as a lidding structure.

Key Features

- Excellent moisture barrier
- Medium oxygen barrier
- Suitable for “see through” packaging structure
- Strong, durable film
- Superior machinability

| PROPERTIES | UNIT | TESTING METHOD | TYPICAL VALUES |
|---|-----------------------------|----------------------------|----------------|
| MECHANICAL | | | |
| Tensile Strength MD TD | lb/in ² | ASTM D882 | 9,500 9,100 |
| Elongation MD TD | % | ASTM D882 | 100 100 |
| PHYSICAL | | | |
| Yield | in ² /lb | | 16,800 |
| COF Sealant side Heat resistant side | | ASTM D1894 | <0.25 0.40 |
| Haze | % | ASTM D1003 | 8 |
| BARRIER | | | |
| MVTR | g/100 in ² /day | ASTM F1249 38°C, 100%RH | 0.4 |
| OTR | cc/100 in ² /day | ASTM D3985 23°C, 0%RH | 6.0 |
| THERMAL | | | |
| Vicat Softening Temperature | F | ASTM D1525 | 220° |

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.