

## LIDDING FILMS



### TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

### CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.  
1762 State Route 131  
Milford, Ohio 45150  
P - 800.634.3355  
F - 513.248.8300

[www.goldeneagleextrusions.com](http://www.goldeneagleextrusions.com)  
[info@goldeneagleextrusions.com](mailto:info@goldeneagleextrusions.com)

# LFO-100TAF

**23 MICRONS/100 GA**  
OTHER THICKNESSES - 53 GA, 80 GA, 144 GA

Our LFO-100TAF an anti-fog lidding film designed to achieve peelable seals to APET, CPET, PVC, modified CPET, PETG, rPET, PLA, PET film, PET coated paperboard and uncoated aluminum. This film is microwaveable and ovenable and can also be frozen or chilled.

	Value	Unit	Standard
Haze	7	%	
Tensile strength MD	26	daN/mm <sup>2</sup>	ASTM D-882
Tensile strength CD	23	daN/mm <sup>2</sup>	ASTM D-882
Elongation MD	135	%	DIN 53455
Elongation CD	95	%	DIN 53455
Shrinkage MD	1.0	%	150°C/mn
Shrinkage CD	- 0.2	%	150°C/mn
Heat Sealing Range	260-410°	°F	
OTR 23°C/0%rH	3.9	cc/100 sq in/ day	
MVTR 37.8°C/90%rH	1.6	g/100 sq in/ day	DIN 53380
Yield @ 100 GA	20,100	SQ. IN./ LB	

**Disclaimer:** Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.