

## LIDDING FILMS



### TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

### CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.  
1762 State Route 131  
Milford, Ohio 45150  
P - 800.634.3355  
F - 513.248.8300

[www.goldeneagleextrusions.com](http://www.goldeneagleextrusions.com)  
[info@goldeneagleextrusions.com](mailto:info@goldeneagleextrusions.com)

# LFO-280PW

## STANDARD THICKNESS - 2.8 MIL

**LFO-280PW** is a white, medium barrier, heat sealable and peelable lidding film. This film is designed to adhere to Polypropylene substrates with a light to medium seal.

### Key Features

- Excellent moisture barrier
- Medium oxygen barrier
- Strong, durable film
- Superior machinability

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
<b>MECHANICAL</b>			
Tensile Strength MD TD	lb/in <sup>2</sup>	ASTM D882	12,000 12,000
Elongation MD TD	%	ASTM D882	100 100
<b>PHYSICAL</b>			
Yield	in <sup>2</sup> /lb		9,900
COF Sealant side Heat resistant side	GRAMS	ASTM D1894	<.35 0.55
<b>BARRIER</b>			
MVTR	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 100%RH	0.4
OTR	cc/100 in <sup>2</sup> /day	ASTM D3985 23°C, 0%RH	6.0
<b>THERMAL</b>			
Vicant Softening Temperature	F	ASTM D1525	270°

**Disclaimer:** Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.