

LAMINATION FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

FHB-33

STANDARD THICKNESS - 3.3 MIL

FHB-33 is a 1235-0 alloy foil laminated to a LLDPE/EVA blend.

- Excellent moisture and oxygen barrier
- One side sealable
- Suitable for wet goods and liquids

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
Yield	in ² /lb		7,900
COF Sealant side	NT/NT	ASTM D1894	≤0.25
BARRIER			
MVTR	g/100 in ² /day	ASTM F1249 38°C, 100%RH	<0.001
OTR	cc/100 in ² /day	ASTM D3985 23°C, 0%RH	<0.001
THERMAL			
Vicat Softening Temperature	F	ASTM D1525	220°

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.