

LIDDING FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

FPL-200A

STANDARD THICKNESS - 2 MIL

FPL-200A is an ultra high barrier and heat sealable lidding film with a specialty PE based sealant layer. This film is designed as a peelable seal to multiple substrates.

Key Features

- Excellent moisture and oxygen barrier
- Suitable for “see through” packaging structure
- One side sealable
- Plain or printed

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
MECHANICAL			
Tensile Strength			
MD	lb/in ²	ASTM D882	29,800
TD			31,200
Elongation			
MD	%	ASTM D882	100
TD			100
PHYSICAL			
Yield	in ² /lb		12,900
COF Sealant side		ASTM D1894	<0.5
Heat resistant side			0.55
Haze	%	ASTM D1003	28
BARRIER			
MVTR	g/100 in ² /day	ASTM F1249 38°C, 100%RH	<0.1
OTR	cc/100 in ² /day	ASTM D3985 23°C, 0%RH	<0.1

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.