

LAMINATION FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

FPL-200

STANDARD THICKNESS - 2.1 MIL

FPL-200 is a high barrier, peelable lidding film designed to adhere to multiple substrates. This lidding film cannot be reheated in any way and is used strictly as a lidding material for fresh foods.

Key Features

- Excellent moisture and oxygen barrier
- Strong, durable film
- Superior machinability
- Great as lidding material for fresh foods

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
MECHANICAL			
Tensile Strength MD TD	lb/in ²	ASTM D882	9,000 9,500
Elongation MD TD	%	ASTM D882	125 115
PHYSICAL			
Yield	in ² /lb		12,300
COF Sealant side Heat resistant side		ASTM D1894	<.40 0.5
Haze	%	ASTM D1003	28
BARRIER			
MVTR	g/100 in ² /day	ASTM F1249 38°C, 100%RH	0.26
OTR	cc/100 in ² /day	ASTM D3985 23°C, 0%RH	0.6
THERMAL			
Vicat Softening Temperature	F	ASTM D1525	220°

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.